


Geosynthetic Institute

475 Kedron Avenue
Folsom, PA 19033-1208 USA
TEL (610) 522-8440
FAX (610) 522-8441



Revision 1: December 19, 2012
Revision Schedule on pg. 9

GRI - GT13(b) – ISO Version Standard Specification*

Standard Specification for

“Test Methods and Properties for Geotextiles Used as Separation Between Subgrade Soil and Aggregate”SM

This specification was developed by the Geosynthetic Research Institute (GRI) with the cooperation of the member organizations for general use by the public. It is completely optional in this regard and can be superseded by other existing or new specifications on the subject matter in whole or in part. Neither GRI, the Geosynthetic Institute, nor any of its related institutes, warrant or indemnifies any materials produced according to this specification either at this time or in the future.

1. Scope

- 1.1 This specification covers geotextile test methods properties for subsequent use as separation between subgrade soil and aggregate predominantly in pavement systems.

Note 1: While separation occurs in every geotextile application, this pavement-related specification focuses on subgrade soils being “firm” as indicated by CBR values higher than 3.0 (soaked) or 8.0 (unsoaked).

- 1.2 This specification sets forth a set of physical, mechanical and endurance properties that must be met, or exceeded, by the geotextile being manufactured.
- 1.3 In the context of quality systems and management, this specification represents a manufacturing quality control (MQC) document. However, its general use is essentially as a recommended design document.
- 1.4 This specification is intended to assure both good quality and performance of fabrics used as geotextile separators but is possibly not adequate for the complete specification in a specific situation. Additional tests, or more restrictive values for the tests indicated, may be necessary under conditions of a particular application.

*This GRI standard specification is developed by the Geosynthetic Research Institute through consultation and review by the member organizations. This specification will be reviewed at least every 2-years, or on an as-required basis. In this regard it is subject to change at any time. The most recent revision date is the effective version and it is kept current on the Institute’s Website <<geosynthetic-institute.org>>.

- 1.5 This standard specification does not address installation practice. This item is addressed in the geosynthetics literature dealing with this particular application and under unique situations might require modifications, e.g., higher values and/or additional test properties.

2. Referenced Documents

2.1 ISO Standards

- ISO 9864 Geosynthetics – Test Method for the Determination of Mass per Unit Area of Geotextiles and Geotextile Related Products
- ISO 11058 Geotextiles – Determination of Water Permeability Characteristics Normal to the Plane, Without Load
- ISO 12236 Geosynthetics – Static puncture test (CBR test)
- ISO 12956 Geotextiles and geotextile – related products – Determination of the characteristic opening size
- ISO 13934 Textiles – Tensile Properties of Fabrics – Part 2: Determination of maximum force using grab method
- ISO 13937 Textiles – Tear Properties of Fabrics – Part 2: Determination of Tear Force of Trouser Shaped Test Specimens

2.2 ASTM Standards

- D 4354 Practice for Sampling of Geosynthetics for Testing
- D 4759 Practice for Determining the Specification Conformance of Geosynthetics
- D 4873 Guide for Identification, Storage and Handling of Geotextiles
- D 7238 Test Method for Effect of Exposure of Unreinforced Polyolefin Geomembrane Using Fluorescent UV Condensation Apparatus

2.3 AASHTO Specification

- M288-05 Geotextile Specification for Highway Applications

3. Definitions

- 3.1 Formulation - The mixture of a unique combination of ingredients identified by type, properties and quantity. For geotextiles, a formulation is defined as the exact percentages and types of resin(s), additives and/or carbon black.
- 3.2 Manufacturing Quality Control (MQC) - A planned system of inspections that is used to directly monitor and control the manufacture of a material which is factory originated. MQC is normally performed by the manufacturer of geosynthetic materials and is necessary to ensure minimum (or maximum) specified values in the manufactured product. MQC refers to measures taken by the manufacturer to determine compliance with the requirements for materials and workmanship as stated in certification documents and contract specifications [ref. EPA/600/R-93/182].

- 3.3 Minimum Average Roll Value (MARV) – For geosynthetics, a manufacturing quality control tool used to allow manufacturers to establish published values such that the user/purchaser will have a 97.7% confidence that the property in question will meet published values. For normally distributed data, “MARV” is calculated as the typical value minus two (2) standard deviations from documented quality control test results for a defined population from one specific test method associated with one specific property.
- 3.4 Minimum Value – The lowest sample value from documented manufacturing quality control test results for a defined population from one test method associated with one specific property.
- 3.5 Maximum Value – The highest sample value from documented manufacturing quality control test results for a defined population from one test method associated with one specific property.
- 3.6 Separation – The placement of a flexible porous geosynthetic between dissimilar materials so the integrity and functioning of both materials can remain intact or be improved.

Note 2: For separation of stone base courses overlying soil subgrades this primary function simultaneously prevents the stone from intruding down into the soil and the soil from pumping up into the stone.

4. Material Classification and Formulation

- 4.1 This specification covers geotextiles used as separation materials.
- 4.2 The polymer types are mainly polypropylene, but also polyester or polyethylene. Other polymers are also possible in this regard.
- 4.3 The type of geotextile style is not designated. However a distinction can be made based on the elongation criteria of 50%.

Note 3: It is assumed that nonwoven fabrics break at elongations higher than 50%. Woven fabrics always break at elongations significantly lower than 50%.

5. Specification Requirements

- 5.1 The geotextiles for use as separator shall conform to Tables 1 or 2. Table 1 is given in SI (Metric) units and Table 2 is in English units. The conversion from English to SI units is “soft”, i.e., rounded off to an approximate value. All test methods are based on ISO or ASTM Standards.

Note 4: The numeric relationships between this specification based on ISO Test Methods and GRI-GT13(a) based on ASTM Test Methods have been developed at the Geosynthetic Institute.

- 5.2 The required values for most properties in Tables 1 and 2 are to be minimum average roll values (MARV). The exceptions are AOS which is a maximum average roll value (MaxARV), and UV stability which is a minimum average value.

Note 5: The ultraviolet incubation method in this specification uses the UV fluorescent exposure device following ASTM D7238. This is done in the absence of a comparable ISO standard. In this regard, GSI does not recommend the Xenon arc device due to both original and maintenance costs resulting in the general absence of such devices in the testing industry. Calibrations between the two devices are available through GSI.

- 5.3 The required class is determined by the severity of installation conditions (i.e., size of equipment, condition of subgrade, thickness of covering lift, etc.). Table 3 gives guidance in this respect.

6. Workmanship and Appearance

- 6.1 The finished geotextile shall have good appearance qualities. It shall be free from such defects that would affect the specific properties of the geotextile, or its proper functioning.
- 6.2 General manufacturing procedures shall be performed in accordance with the manufacturer's internal quality control guide and/or documents.

7. MQC Sampling, Testing, and Acceptance

- 7.1 Geotextiles shall be subject to sampling and testing to verify conformance with this specification. Sampling shall be in accordance with the most current modification of ASTM Standard D 4354, using the section titled, "Procedure for Sampling for Purchaser's Specification Conformance Testing." There is no current ISO Standard on this topic. In the absence of purchaser's testing, verification may be based on manufacturer's certifications as a result of testing by the manufacturer of quality assurance samples obtained using the procedure for Sampling for Manufacturer's Quality Assurance (MQA) Testing. A lot size shall be considered to be the shipment quantity of the given product or a truckload of the given product, whichever is smaller.
- 7.2 Testing shall be performed in accordance with the method referenced in this specification for the indicated application. The number of specimens to test per sample is specified by each test method. Geotextile product acceptance shall be based on ASTM D4759. Product acceptance is determined by comparing the average test results of all specimens within a given sample to the specification MARV. Refer to ASTM D 4759 for more details regarding geotextile acceptance procedures. There are no current ISO Standards on these topics.

8. MQC Retest and Rejection

8.1 If the results of any test do not conform to the requirements of this specification, retesting to determine conformance or rejection should be done in accordance with the manufacturing protocol as set forth in the manufacturer's quality manual.

9. Shipment and Storage

9.1 Geotextile labeling, shipment, and storage shall follow ASTM D 4873. There is no current ISO Standard on this topic. Product labels shall clearly show the manufacturer or supplier name, style, and roll number. Each shipping document shall include a notation certifying that the material is in accordance with the manufacturer's certificate.

9.2 Each geotextile roll shall be wrapped with a material that will protect the geotextile, including the ends of the roll, from damage due to shipment, water, sunlight and contaminants. The protective wrapping shall be maintained during periods of shipment and storage.

Note 6: The project specification shall be very explicit as to the maximum exposure time between the geotextile being removed from the wrapper and being backfilled with soil or covered with another geosynthetic.

9.3 During storage, geotextile rolls shall be elevated off the ground and adequately covered to protect them from the following: site construction damage, precipitation, extended ultraviolet radiation including sunlight, chemicals that are strong acids or strong bases, flames including welding sparks, temperatures in excess of 70°C (158°F), and any other environmental condition that may damage the property values of the geotextile.

10. Certification

10.1 The contractor shall provide to the engineer a certificate stating the name of the manufacturer, product name, style number, chemical composition of the filaments or yarns, and other pertinent information to fully describe the geotextile.

10.2 The manufacturer is responsible for establishing and maintaining a quality control program to assure compliance with the requirements of the specification. Documentation describing the quality control program shall be made available upon request.

10.3 The manufacturer's certificate shall state that the finished geotextile meets the requirements of the specification as evaluated under the manufacturer's quality control program. A person having legal authority to bind the manufacturer shall attest to the certificate.

10.4 Either mislabeling or misrepresentation of materials shall be reason to reject those geotextile products.

SI Metric Units

Table 1(a) – Geotextile Properties Class 1 (High Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	N	1250	800
Trouser Tear Strength	ISO 13937-2	N	425	300
CBR Puncture Strength	ISO 12236	N	2800	2000
Permeability	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	80	80

Table 1(b) – Geotextile Properties Class 2 (Moderate Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	N	1000	630
Trouser Tear Strength	ISO 13937-2	N	340	210
CBR Puncture Strength	ISO 12236	N	2250	1400
Permeability	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	70	70

Table 1(c) – Geotextile Properties Class 3 (Low Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	N	750	450
Trouser Tear Strength	ISO 13937-2	N	250	150
CBR Puncture Strength	ISO 12236	N	1700	1000
Permeability	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	60	60

Notes:

- (1) All values are minimum average roll values (MARV) except AOS which is a maximum average roll value (MaxARV) and UV stability which is a minimum average value.
- (2) Evaluation to be on 50 mm strip tensile specimens after 500 hours exposure.

English Units

Table 2(a) – Geotextile Properties Class 1 (High Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	lb	280	180
Trouser Tear Strength	ISO 13937-2	lb	95	70
CBR Puncture Strength	ISO 12236	lb	630	440
Permittivity	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	80	80

Table 2(b) – Geotextile Properties Class 2 (Moderate Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	lb	225	140
Trouser Tear Strength	ISO 13937-2	lb	75	50
CBR Puncture Strength	ISO 12236	lb	500	320
Permittivity	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	70	70

Table 2(c) – Geotextile Properties Class 3 (Low Survivability)

Property ⁽¹⁾	Test Method	Unit	Elongation < 50%	Elongation ≥ 50%
Grab Tensile Strength	ISO 13934-2	lb	170	100
Trouser Tear Strength	ISO 13937-2	lb	55	35
CBR Puncture Strength	ISO 12236	lb	380	230
Permittivity	ISO 11058	m/sec	0.01	0.01
Apparent Opening Size	ISO 12956	micron	500	500
Ultraviolet Stability ⁽²⁾	ASTM D 7238	% Str. Ret. @ 500 lt. hrs.	6	60

Notes:

- (1) All values are minimum average roll values (MARV) except AOS which is a maximum average roll value (MaxARV) and UV stability which is a minimum average value.
- (2) Evaluation to be on 50 mm strip tensile specimens after 500 hours exposure.

Table 3 - Required Degree of Survivability as a Function of Subgrade Conditions, Construction Equipment and Lift Thickness
(Class 1, 2 and 3 Properties are Given in Table 1 and 2; Class 1 + Properties are Higher than Class 1 but Not Defined at this Time)

	Low ground-pressure equipment ≤ 25 kPa (3.6 psi)	Medium ground-pressure equipment > 25 to ≤ 50 kPa (>3.6 to ≤ 7.3 psi)	High ground-pressure equipment > 50 kPa (> 7.3 psi)
Subgrade has been cleared of all obstacles except grass, weeds, leaves, and fine wood debris. Surface is smooth and level so that any shallow depressions and humps do not exceed 450 mm (18 in.) in depth or height. All larger depressions are filled. Alternatively, a smooth working table may be placed.	Low (Class 3)	Moderate (Class 2)	High (Class 1)
Subgrade has been cleared of obstacles larger than small to moderate-sized tree limbs and rocks. Tree trunks and stumps should be removed or covered with a partial working table. Depressions and humps should not exceed 450 mm (18 in.) in depth or height. Larger depressions should be filled.	Moderate (Class 2)	High (Class 1)	Very High (Class 1+)
Minimal site preparation is required. Trees may be felled, delimbed, and left in place. Stumps should be cut to project not more than ± 150 mm (6 in.) above subgrade. Fabric may be draped directly over the tree trunks, stumps, large depressions and humps, holes, stream channels, and large boulders. Items should be removed only if placing the fabric and cover material over them will distort the finished road surface.	High (Class 1)	Very high (Class 1+)	Not recommended

*Recommendations are for 150 to 300 mm (6 to 12 in.) initial lift thickness. For other initial lift thicknesses:

- 300 to 450 mm (12 to 18 in.): reduce survivability requirement one level;
- 450 to 600 mm (18 to 24 in.): reduce survivability requirement two levels;
- > 600 mm (24 in.): reduce survivability requirement three levels

Note 1: While separation occurs in every geotextile application, this pavement-related specification focuses on subgrade soils being “firm” as indicated by CBR values higher than 3.0 (soaked) or 8.0 (unsoaked).

Source: Modified after Christopher, Holtz, and DiMaggio

Adoption and Revision Schedule

GRI-GT13(b) – ISO Version

“Test Methods and Properties for Geotextiles Used as Separation Between Subgrade Soil and Aggregate”

Original: September 29, 2008

Revision 1: December 19, 2012: Replaced EN 12224 with ASTM D7238 exposure device and editorial changes